

TECAFINE ® PP - Stock Shapes (rods, plates, tubes)

Chemical Designation

PP (Polypropylene)

Colour white

Density 0.9 g/cm³

Main features

- → excellent chemical resistance
- → high purity
- → good mechanical properties
- → very low water absorption

Target Industries

- → chemical plant engineering
- → cleanroom technology
- → food processing
- → food engineering
- pharmaceutical industry
- → filter technology
- → nuclear and vacuum technology

Mechanical properties	condition	value		test method		comment
Modulus of elasticity (tensile test)	@ 73 °F	105,000	psi	ASTM D 638		
Tensile strength at break	@ 73 °F	3,900	psi	ASTM D 638		•••
Elongation at break	@ 73 °F	500	%	ASTM D 638		•••
Flexural strength	@ 73 °F	4,500	psi	ASTM D 790		
Modulus of elasticity (flexural test)	@ 73 °F	165,000	psi	ASTM D 790		
Notched impact strength (Izod)	@ 73 °F	2.1	ft-lbs/in	ASTM D 256		•••
Rockwell hardness	R Scale	102		ASTM D 785		
Rockwell hardness	M Scale, @ 73 °F	95	_	-		
Thermal properties	condition	value		test method		comment
Melting temperature		297	°F	-	1)	(1) per ASTM D3418 ···· (2) Resin data
Deflection temperature	@66 psi	165	°F	ASTM D 648	2)	
Other properties	condition	value		test method		comment
Moisture absorption	@ 24 hrs, 73 °F	0.06	%	ASTM D 570		

[→] Resin specification: ASTM D4101-10a PP0210 Shapes specification: NONE

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters 365 Meadow lands Boulevard Washington, PA 15301, USA Phone 800-243-3221 Sales Phone 800-869-4029 Technical Fax 724-746-9209 sales@ensinger-ind.com Date: 2017/10/04

Version: A1